

[ View Image ]

**JP7096575 - LAMINATE AND ITS PRODUCTION**

Publication number	Publication date	Application number	Application date
JP7096575	11 April 1995	JP19930243321	29 September 1993

**Priority:****Equivalents:**

JP3049178B2 [Order equivalents]

**Applicant(s) / Assignee (s):**

TOKAI RUBBER IND LTD

**Inventor(s):**

MURAKAMI KOYO

others: 03

**IPC:**

B32B9/04 B32B27/16 B32B27/30 B32B27/34

C08J7/00

**Abstract:**

**PURPOSE:** To obtain a low-cost laminate having a superior bonding strength and a laminate superior in safety with a high production efficiency by a method wherein a laminating surface of a fluoro resin layer is roughened, and on the roughened surface a layer treated with a specific coupling agent is formed.

**CONSTITUTION:** In a laminate, a thermoplastic polyamide resin layer 15 is laminated on a surface of a fluoro resin layer 10.

Namely, the laminating surface of the fluoro resin layer 10 is roughened, and on the roughened surface a layer 16 treated with an aminosilane coupling agent is formed.

It is preferable that the laminating surface of the fluoro resin layer 10 is roughened by a corona discharge treatment.

In a method for producing the laminate, the surface of the fluoro resin layer 10 is subjected to a corona discharge treatment, the layer 16 treated with an aminosilane coupling agent is formed on the discharge-treated surface, and the fluoro resin layer and the thermoplastic polyamide resin layer are bonded to each other with the aminosilane-treated layer facing the surface of the latter.

